

# **Cutting fluid DK-760C6**

#### [ Performance and use ]

Dremfu DK-760C6 water-soluble grinding fluid is prepared by a variety of surfactants, lubricants, anti-rust agents and other additives. It is suitable for wire-cut cooling processing of glass-ceramics, quartz, optical glass and other materials.

# [ Main technical parameters ]

item	Technical indicators	Test method
External view	Light yellow transparent	Eye survey
	ilquid	
pH value	9.5 ± 0.5	GB6144-85
Defoaming (ml)	2 or less	GB6144-85
Specific weight (g/ml)	1.10 ± 0.10	hydrometer
Surface tension (dyn/cm)	30 or less	GB6144-85
Storage stability	conjunctive	GB6144-85
corrosiveness	Grade A cast iron	GB6144-85
Rust resistance	Grade A cast iron	GB6144-85

## [ Product advantage ]

- Excellent lubricity, cooling and cleaning.
- Environmentally friendly and not harmful to skin.
- Excellent powder sedimentation.
- not corrupt, long service life.

#### [ Instruction ]

- 1. The working liquid is diluted with 10-20 times tap water or deionized water.
- 2. During use, the working liquid consumed can be supplemented at a concentration of 3-5%.
- 3. Avoid mixing with other oils.



# [ Packaging ]

18L/ barrel, 25L/ barrel, 200L/ barrel.

## [ Note ]

- 1. This product should not be mixed with other emulsions, semi-synthetic liquids, and fully synthetic liquids, because even if the system contains a small amount of rotten residual liquid, it will affect the use effect of the new liquid.
- 2.the production batch is not the same, the cutting fluid may have color differences, does not affect the normal use.